

<p>Applications</p>	<p>Applied to the prepared surface with a trowel or by hand at the required thickness, from 3mm upwards, depending upon the application.</p> <p>Lining of:</p> <ul style="list-style-type: none"> ➤ pipe bends ➤ slurry lines ➤ pump casing ➤ cyclones ➤ conveyor pulleys ➤ chutes, hoppers ➤ launders and feeder boxes
<p>Description</p>	<p>100% solids modified epoxy resin system containing sapphire hard fused alumina ceramic beads to withstand severe cavitation, tough abrasion and moderate impact.</p>
<p>Theoretical Coverage</p>	<p>12kg Kit covers 1m² at 6mm thick not compacted and 4.2mm thick - compacted</p>
<p>Surface Preparation</p>	<p>A properly prepared surface is important to the result and lasting durability of ENVIROWEAR 362. Steel surfaces should be dry grit blasted to SA 2.5 with blast profile between 50-70 microns to leave the surface free of oil and grease contamination. In cold conditions it is recommended to warm the substrate to 20-35°C.</p>
<p>Kit Size</p>	<p>12 kg Kits</p>

