

<p><b>Applications</b></p>	<p>Applied to the prepared surface with a trowel or by hand at the required thickness, from 3mm upwards, depending upon the application.</p> <p>Lining of:</p> <ul style="list-style-type: none"> <li>➤ pipe bends</li> <li>➤ slurry lines</li> <li>➤ pump casing</li> <li>➤ cyclones</li> <li>➤ conveyor pulleys</li> <li>➤ chutes, hoppers</li> <li>➤ launders and feeder boxes</li> </ul>
<p><b>Description</b></p>	<p>100% solids modified epoxy resin system containing sapphire hard fused alumina ceramic beads to withstand severe cavitation, tough abrasion and moderate impact.</p>
<p><b>Theoretical Coverage</b></p>	<p>12kg Kit covers 1m<sup>2</sup> at 6mm thick not compacted and 4.2mm thick - compacted</p>
<p><b>Surface Preparation</b></p>	<p>A properly prepared surface is important to the result and lasting durability of ENVIROWEAR 363 CH. Steel surfaces should be dry grit blasted to SA 2.5 with blast profile between 50-70 microns to leave the surface free of oil and grease contamination. In cold conditions it is recommended to warm the substrate to 20-35°C.</p>
<p><b>Kit Size</b></p>	<p>10 kg Kits</p>

